



bioVis

VISCOELASTIC
SOLUTIONS
for intraocular use

MEDICENTUR



VISCOELASTIC SOLUTIONS FOR INTRAOCULAR USE

PRODUCT	BioVis 1.6%	BioVis 1.8%	BioVis 3.0%
CONCENTRATION	16 mg/ml	18 mg/ml	30 mg/ml
STRUCTURE	Cohesive	Cohesive	Dispersive
ORIGIN	Biofermented	Biofermented	Biofermented
MOLECULAR WEIGHT	Appr. 3.0MDa	Appr. 3.0MDa	Appr. 0.75MDa
ZERO SHEAR VISCOSITY	400.000 mPas	600.000 mPas	30.000 mPas
OSMOLALITY	300 – 350 mOsm/kg	300 – 350 mOsm/kg	300 – 350 mOsm/kg
PH VALUE	6.8 – 7.6	6.8 – 7.6	6.8 – 7.6
VOLUME	1.1 ml	1.1 ml	1.1 ml
CANNULA	27G	27G	25G
STERILIZATION METHOD	Steam & ETO	Steam & ETO	Steam & ETO
STORAGE CONDITION	2–25° C	2–25° C	2–25° C



MA-IOL-BIOVI-MD016-INF-HU 202304

MEDICENTUR

Medicentur
Medical Engineering Ltd
export@medicentur.com
www.medicentur.com

Head Office
Herceghalmi út 1.
2072 Zsámbék
Hungary

International Office
Chemin du Champ-des-Filles 36
1228 Plan-les-Ouates
Geneva / Switzerland

CE
1639